

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
3 June 2004 (03.06.2004)

PCT

(10) International Publication Number
WO 2004/045838 A1

(51) International Patent Classification⁷: B29D 30/06,
30/00

(21) International Application Number:
PCT/IB2002/004833

(22) International Filing Date:
20 November 2002 (20.11.2002)

(25) Filing Language: Italian

(26) Publication Language: English

(71) Applicant (for all designated States except US): PIRELLI
PNEUMATICI S.P.A. [IT/IT]; Viale Sarca, 222, I-20126
Milano (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): CANTU', Marco

[IT/IT]; Via Fornace, 9, I-20040 Carnate (IT). CASALI,
Andrea [IT/IT]; Via Toselli, 57, I-20091 Bresso (IT).
MISANI, Pierangelo [IT/IT]; Via Oslavia, 30, I-20052
Monza (IT). PIANTANIDA, Pier, Giuseppe [IT/IT];
Via Raspagna, 5, I-28047 Oleggio (IT). AZZARETTO,
Riccardo [IT/IT]; Viale Suzzani, 269, I-20162 Milano
(IT).

(74) Agents: BOTTERO, Carlo et al.; Pirelli S.p.A., Viale
Sarca, 222, I-20126 Milano (IT).


(81) Designated State (national): US.

Published:

- with international search report
- upon request of the applicant under Article 64(3)(c)(i)

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD AND APPARATUS FOR MOLDING AND CURING A TYRE FOR VEHICLE WHEELS



(57) Abstract: A method of molding and curing a tyre for vehicle wheels comprises the steps of: building a green tyre (50) on a toroidal support (10) having an outer surface substantially conforming in shape to the inner surface of said green tyre (50); heating said toroidal support (10) to transmit heat to the inner surface of the tyre in contact with said toroidal support (10); pressing said inner surface of said green tyre (50) against said outer surface of said toroidal support (10) by means of at least one secondary working fluid under pressure; pressing an outer surface of said green tyre (50) against the walls of a molding cavity (104) defined in a vulcanisation mold (102), by means of a primary working fluid under pressure passing in at least one diffusion gap between said outer surface of said toroidal support (10) and said inner surface of said green tyre (50); said primary working fluid under pressure being heated so as to supply heat to said green tyre (50) in order to cause vulcanisation of same.

WO 2004/045838 A1

METHOD AND APPARATUS FOR MOLDING AND CURING A TYRE FOR
VEHICLE WHEELS

D e s c r i p t i o n

5

The present invention relates to a method and an apparatus for molding and curing a tyre for vehicle wheels.

- 10 In a tyre production cycle it is provided that following a building process in which the different tyre components are made and/or assembled, a molding and curing process is carried out which aims at
15 defining the tyre structure in accordance with a desired geometry, usually exhibiting a particular tread pattern.

- For the purpose, the tyre is closed in a molding cavity defined internally of a vulcanisation mold and shaped
20 in accordance with the geometric configuration of the outer surfaces of the tyre to be obtained.

- A tyre generally comprises a toroidally ring-shaped carcass including one or more carcass plies,
25 strengthened with reinforcing cords lying in radial planes, i.e. containing the rotation axis of the tyre. Each carcass ply has its ends integrally associated with at least one annular reinforcing metal structure, usually known as bead core, constituting the
30 reinforcing piece at the beads, i.e. at the radially internal ends of said tyre, the function of which is to enable assembling of the tyre with a corresponding mounting rim. Placed crownwise to said carcass is a band of elastomer material, called tread band, in which
35 at the end of the curing and vulcanisation steps a

raised pattern is formed for ground contact. A reinforcing structure usually known as belt structure is placed between the carcass and tread band. This structure in the case of tyres for cars usually
5 comprises at least two radially superposed strips of rubberised fabric provided with reinforcing cords, usually of metal material, disposed parallel to each other in each strip and in crossed relationship with the cords of the adjacent strip, preferably
10 symmetrically disposed with respect to the equatorial plane of the tyre.

Preferably, said belt structure further comprises, at a radially external position thereof, at least on the
15 ends of the underlying strips, a third layer of textile or metallic cords as well, that are disposed circumferentially (at 0 degrees).

Finally, in tyres of the tubeless type i.e. devoid of
20 an air tube, a radially internal layer generally called liner is present which has imperviousness features to ensure the tyre air-tightness.

To the aims of the present invention it is to be
25 pointed out that by the term "elastomer material" it is intended a composition comprising at least one elastomer polymer and at least one reinforcing filler. Preferably, this composition further comprises additives, such as cross-linking and/or plasticizing
30 agents, for example. By virtue of the presence of the cross-linking agents, this material can be cross-linked through heating, so as to form the final manufactured article.

35 There are molding and curing methods in which a green

- tyre put on a rigid toroidal support is arranged within the mold. Said methods are preferably employed for tyres that, following recent building processes, are produced starting from a limited number of elementary
- 5 semifinished products fed onto a toroidal support the outer profile of which is coincident with that of the radially internal surface of the tyre that is wished to be produced. Said toroidal support is moved, preferably by a robotized system, between a plurality of stations
- 10 in each of which, through automated sequences, a particular building step of the tyre is carried out (see document EP 0 928 680 in the name of the same Applicant, for example).
- 15 The European Patent Application published under No. 0 976 533 in the name of the same Applicant discloses a method and an apparatus for molding and curing tyres for vehicle wheels in which the green tyre built on a toroidal support is closed in a vulcanisation mold;
- 20 subsequently steam or other fluid under pressure is fed into at least one gap for fluid diffusion created between the outer surface of the toroidal support and inner surface of the tyre.
- 25 The Applicant could verify that by a method of the above illustrated type, at the end of the molding and curing step, the obtained tyre may sometimes exhibit some faults. This mainly takes place because the working fluid (i.e. the vulcanisation fluid) comes
- 30 directly into contact with the innermost layer of the tyre, since for tyres directly assembled and cured on the same toroidal support there is not the effect of the vulcanisation bladder. Said bladder when it is present within the green tyre in the vulcanisation
- 35 mold, allows a uniform distribution of the elastomer

material against the mold also correcting small working faults due to junctions, slight manual errors or errors of the building drum, for example. In fact, it should be remembered that in traditional building processes, 5 i.e. when semifinished products even of great sizes (such as carcass plies, belt strips, tread band, for example) are assembled on cylindrical building drums and the green tyre is shaped into a toroidal conformation by appropriate devices (mechanical or 10 pneumatic devices, for example) associated with the drums themselves, at the end of the working operation green tyres are obtained that are disengaged from their building and shaping drum/s and can therefore internally house said vulcanisation bladder.

15 In particular, the Applicant could ascertain during molding and curing of the tyres directly built on a toroidal support that, while the working fluid under pressure is fed between the outer surface of the 20 toroidal support and the inner surface of the green tyre, the various components of elastomer material still in an uncured state, i.e. in a plastic state, can take an anomalous arrangement with respect to the design specifications. In particular, the carcass ply 25 or plies can move away from their position in the bead region and slip off due to the expansion to which the tyre is submitted by said working fluid. In this way tensioning of the carcass ply or plies determined by the molding step is lower than it is provided to be for 30 the finished tyre.

In the same manner as the carcass ply, other components of the green tyre can slide relative to each other due to the inner vulcanisation pressure during the first 35 minutes of this process, i.e. when the plastic features

- 5 -

of the elastomer material are more present. This phenomenon is more felt in the bead region, where in addition to partial slipping off of the carcass plies, phenomena of lack or accumulation of material are
5 observed that give rise to formation of steps and discontinuities on the bead itself.

The Applicant has perceived that by at least partly fixing the geometry of the beads and the innermost
10 surface of the tyre, i.e. that tyre portion in contact with the toroidal support that is the first to come into contact with the working fluid during vulcanisation, the above mentioned drawbacks can be overcome.

15

In more detail the Applicant has found that by pressing the green tyre from the outside to the inside and simultaneously supplying heat to the inner surface of said tyre, at least partial vulcanisation of the
20 innermost layer of the tyre and of the bead region is obtained, so that a molding and curing step can be subsequently performed without involving lack of homogeneity and irregularities in the finished tyre.

25 In fact the working fluid under molding and curing conditions is in direct contact with parts of the tyre that have already been partly vulcanised and therefore no longer exhibit a plastic behaviour of the material but an almost elastic one. In this case it is obtained
30 a uniform distribution against the mold of the elastomer material belonging to the outermost tyre layers. In addition tension of the carcass ply or plies due to the vulcanisation pressure does not cause any slipping off of the plies at the beads, since the ply
35 or plies have become substantially integral with the

elastomer materials present in this region following partial vulcanisation of same.

In a first aspect, the invention relates to a method of
5 molding and curing a tyre for vehicle wheels comprising
the steps of: building a green tyre on a toroidal
support having an outer surface the shape of which
substantially matches that of an inner surface of said
green tyre; heating said toroidal support to transmit
10 heat to the inner surface of the tyre in contact with
said toroidal support; pressing said inner surface of
said green tyre against said outer surface of said
toroidal support through at least one secondary working
fluid under pressure; pressing an outer surface of said
15 green tyre against the walls of a molding cavity
defined in a vulcanisation mold, through a primary
working fluid under pressure passing in at least one
diffusion gap between said outer surface of said
toroidal support and said inner surface of said green
20 tyre; said primary working fluid under pressure being
heated so as to supply heat to said green tyre to cause
vulcanisation thereof.

In a second aspect the invention relates to an
25 apparatus for molding and curing a tyre for vehicle
wheels, said apparatus comprising: an airtight
vulcanisation mold arranged to receive a toroidal
support adapted to support a green tyre within a
molding cavity; at least one passage device adapted to
30 feed at least one primary working fluid under pressure,
which is formed through said toroidal support and opens
onto the outer surface of same, so as to enable passage
of said primary working fluid under pressure towards
the inner surface of said green tyre; a feeding device
35 to supply a secondary working fluid under pressure

which is operatively associated with said vulcanisation mold to press said green tyre from the outside to the inside onto said outer surface of said toroidal support; heating devices to heat said toroidal support; heating devices to heat said primary working fluid to transmit heat to said green tyre and cause vulcanisation of same.

In a third aspect, the invention relates to an apparatus for molding and curing a tyre for vehicle wheels, said apparatus comprising: a vulcanisation mold arranged to receive a toroidal support adapted to support a green tyre within a molding cavity; at least one passage device, adapted to feed at least one primary working fluid under pressure, which is formed through said toroidal support and opens onto the outer surface of same, so as to enable passage of said primary working fluid under pressure to the inner surface of said green tyre; heating devices to heat said primary working fluid to transmit heat to said green tyre and cause vulcanisation of same; an airtight container arranged to receive said toroidal support; a feeding device to supply a secondary working fluid under pressure which is operatively associated with said airtight container for pressing said green tyre from the outside to the inside onto said outer surface of said toroidal support; heating devices to heat said toroidal support.

Further features and advantages of the invention will become more apparent from the detailed description of some preferred, but not exclusive, embodiments of a method and an apparatus for molding and curing a tyre for vehicle wheels in accordance with the present invention.

This description will be set out hereinafter with reference to the accompanying drawings, given by way of non-limiting example, in which:

- 5 - Fig. 1 is a vertical view partly in section of a preferred embodiment of the apparatus in accordance with the invention during a step of the method in question;
 - Fig. 2 is a vertical view partly in section of a preferred embodiment of the apparatus in accordance with the invention during a further step of the method in question;
 - 10 - Fig. 3 is a vertical view partly in section of a device belonging to an embodiment of the apparatus in accordance with the invention;
 - 15 - Fig. 4 is a diagram showing the course of pressure over time in relation to the working fluids employed for carrying out the concerned method.
- 20 With reference to Fig. 1, a molding and curing apparatus for vehicle wheel tyres in accordance with a first embodiment of the present invention has been generally identified by reference numeral 101.
- 25 Apparatus 101 comprises a vulcanisation mold 102 operatively associated with an airtight container 103.

Preferably, the mold 102 can be made up of a lower half 102A and an upper half 102B, in engagement with a base 103A and a closing portion 103B of container 103, respectively.

In the embodiment shown by way of example, each of the lower 102A and upper 102B halves of mold 102 has a cheek, a lower cheek 130A and an upper cheek 130B

respectively, and a crown of sectors consisting of a lower sector 131A and an upper sector 131B, respectively.

5 The lower 102A and upper 102B halves are mutually movable between an open position at which they are spaced apart from each other, and a closed position shown in Figs. 1 and 2, at which they are close to each other to form a molding cavity 104 the inner walls of
10 which defined by said cheeks and said sectors reproduce the geometric configuration of the outer surface of a tyre to be obtained at the end of the molding and vulcanisation steps.

15 In more detail, the cheeks are designed to form the outer surfaces of the opposite tyre sidewalls, whereas the sectors are designed to form the so-called tread band of the tyre itself, by creating therein a series of cuts and longitudinal and/or transverse grooves
20 suitably disposed in accordance with a desired "tread pattern".

Apparatus 101 further contemplates use of at least one toroidal support 10 of metal or other rigid material,
25 having an outer surface substantially reproducing the shape of the inner surface of the tyre. The toroidal support 10 is conveniently made up of a drum that can be dismantled, i.e. made up of circumferential segments at least some of which are centripetally movable to
30 take the toroidal support to pieces and enable easy removal of same from the tyre when working is over.

Apparatus 101 further comprises at least one duct 110 (Fig. 2) for a primary working fluid under pressure
35 such as steam, nitrogen or other substantially inert

gas or a mixture thereof, which fluid is used as better illustrated in the following, for molding and vulcanisation of the tyre.

- 5 Also preferably present in apparatus 101 are heating devices for the mold 102 preferably in the form of a plurality of ducts 105 for passage of a heating fluid.

Preferably, apparatus 101 also comprises an airtight
10 device adapted to contain the toroidal support 10 on which a green tyre 50 has been previously built.

As shown in Figs. 1 and 2, said airtight device in a preferred embodiment can be enclosed and integrated
15 into said mold 102, defining an airtight cavity within the same. Preferably in this case said mold 102 comprises a plurality of seals 106 disposed close to vents for escape of the primary working fluid employed for vulcanisation of said tyre, and at least one
20 circumferential seal 107 placed on the opposite surfaces of the two halves 102A and 102B.

Said circumferential seal 107 may consist of an O-ring or preferably a series of superposed metal rings
25 provided between their opposite surfaces, with a sealing element capable of withstanding the pressures and temperatures of the method described in the following.

30 A feeding device for a secondary working fluid is operatively associated, in this embodiment, with said mold 102. Said device comprises at least one delivery duct 108 and one discharge duct 109 to respectively feed and evacuate said secondary working fluid under
35 pressure, such as air, nitrogen or other substantially

inert gases within said mold 102, to press the inner surface of said green tyre 50 from the outside to the inside, as better described in the following, against the outer surface of said toroidal support 10.

5

Alternatively, an airtight device 200 may be provided (Fig. 3) externally of the mold itself. Said device will substantially be of the same outer shape as mold 102 shown in Figs. 1 and 2, but obviously neither
10 cheeks 130A and 130B nor sectors 131A and 131B illustrated above, i.e. those parts intended for tyre molding, will be present therein. More specifically, said device 200 comprises one lower half 202A and one upper half 202B, in engagement with a base 203A and a
15 closing portion 203B respectively and at least one circumferential seal 207 put on the opposite surfaces of the two halves 202A and 202B. Also provided in said device 200 and in association therewith is a feeding device for a secondary working fluid comprising at
20 least one delivery duct 208 and one discharge duct 209 to respectively feed and evacuate said secondary working fluid under pressure such as air, nitrogen and other substantially inert gases within said device 200, to press the inner surface of said green tyre 50 from
25 the outside to the inside, as better described in the following, against the outer surface of said toroidal support 10.

Optionally, said device 200 may provide at least one
30 duct 210 for said primary working fluid under pressure, which fluid is employed, as better described later on, to heat the outer surface of said toroidal support 10.

In addition, when said device 200 is present, an
35 airtight mold as above described in connection with

Figs. 1 and 2 is not required in apparatus 101.

Duct 110 (or 210) is operatively associated with at least one passage device, through a connecting duct
5 (not shown) for example, formed along at least one of the centering shanks of said toroidal support 10, to enable diffusion of said primary working fluid under pressure within said toroidal support 10.

10 Said passage device comprises suitable branches formed in the toroidal support 10, through which said primary working fluid reaches a plurality of ducts opening onto the outer surface of the toroidal support itself, conveniently distributed and sizes on the
15 circumferential extension thereof. Distribution and sizes will be of such a nature that introduction of raw elastomer material into said toroidal support 10 is prevented.

20 Preferably, a duct 111 adapted to discharge possible condensate is then provided at the lower part of said molding cavity 104.

In accordance with the method of the invention, the
25 green tyre 50 is disposed on the toroidal support 10 before the latter is inserted, together with the tyre, into the airtight vulcanisation mold 102 arranged in an open condition or into said airtight device 200 if it is de-coupled from said mold.

30

In particular, engagement of the tyre on the toroidal support 10 can be conveniently obtained by building the tyre directly on the support itself. In this way the toroidal support 10 is advantageously utilised as a
35 rigid core for deposition of the different components

- 13 -

such as liner, carcass plies, reinforcing structures at the beads, belt strips, sidewalls and tread band that concur in tyre formation. More specifically, said tyre components are preferably obtained by deposition on
5 said toroidal support 10 of semifinished products such as, by way of example, strips of elastomer material, strip-like elements of elastomer material internally comprising a plurality of textile or metallic cords, metal cords preferably made of high tensile steel.
10 Further features on the procedure of laying down the tyre components onto the toroidal support 10 are described in the European Patent Application published under No. 0 929 680 in the name of the same Applicant, for example.

15
Operation of apparatus 101, once said toroidal support 10 carrying the green tyre 50 has been placed into said mold 102 (or said airtight device 200), involves closure of the apparatus itself and starting of the
20 molding and curing operations.

More specifically, by duct 108 (or 208) said secondary fluid under pressure (identified with "b" in Fig. 4) is sent into a cavity included between the outer surface
25 of said green tyre 50 and the inner surface of said mold 102 (or said device 200). Substantially simultaneously, as shown in Fig. 4, by duct 110 (or 210) said primary working fluid under pressure (identified with "a" in Fig. 4) is sent into said
30 toroidal support 10 to a lower pressure than that of said secondary working fluid. The transient has a duration included between 30 seconds and 1 minute; in a steady-state condition and for a duration of 30 seconds to 6 minutes, the pressure differential is lower than
35 10 bars, preferably of about 1-2 bars. Since the

primary working fluid is of lower pressure, it will remain within said toroidal support 10 without escaping through the previously illustrated ducts. In this way during this step the green tyre 50 is pressed
5 from the outside to the inside so that its inner surface preferably comprising the liner is pressed against the outer surface of the toroidal support 10.

Preferably said secondary working fluid is fed at room
10 temperature, at a pressure generally included between 8 and 18 bars, while said primary working fluid, in this step preferably formed of steam, is fed to a pressure lower than 16 bars and a temperature generally included between approximately 170°C and 210°C.

15

In the example shown in fig. 4, the transient lasts about one minute, pressure of the secondary working fluid in a steady-state condition is about 16 bars and pressure of the primary working fluid is about 14 bars,
20 the differential pressure therefore being about 2 bars.

As above illustrated, in a steady-state condition this step lasts some minutes (about two in the example shown in Fig. 4). During this period of time the primary
25 working fluid heats the toroidal support 10 which transmits heat to the inner surface of the tyre, and consequently to the bead region and preferably the liner. This heating does not fully cure said parts of the tyre but at all events it is sufficient to give the
30 parts themselves features of elasticity. In particular, the carcass ply or plies are well anchored to the beads and the inner tyre surface, preferably the liner, becomes elastic enough to withstand the subsequent pressure of the molding and vulcanisation process
35 illustrated in the following, without tearing.

Termination of this step involves evacuation of the secondary working fluid through the discharge duct 109 (or 209), preferably in a period of time shorter than 2 minutes (1 minute in the example shown).

5

If mold 102 is airtight, a subsequent step immediately starts for molding and fully curing said tyre (as shown in Figs. 2, 4). Said step begins through raising of said primary-working fluid pressure to a value included
10 between 18 and 35 bars, preferably 26-28 bars, for the purpose of molding and curing the tyre with the desired tensioning on the carcass ply.

In this step the primary working fluid preferably
15 comprises a steam-nitrogen mixture, although it may consist of steam alone or steam admixed with air or other substantially inert gases, or one or more gases such as air, nitrogen and other substantially inert gases.

20

Pressure generated by said primary working fluid reaches a diffusion gap created between the outer surface of the toroidal support 10 and the inner surface of the tyre to be cured.

25

In a preferential embodiment, the diffusion gap is directly created following a tyre expansion caused by effect of the thrust exerted by said primary working fluid. In other words, pressing of the tyre against the
30 walls of the molding cavity 104 takes place concurrently with an expansion imposed to the tyre itself, until bringing the outer surface thereof to fully adhere to the inner walls of the molding cavity 104. Then said pressing operation takes place
35 simultaneously with administration of heat to produce

- 16 -

cross-linking of the elastomer material forming the tyre itself and consequent geometric and structural definition of the latter. Advantageously, said primary working fluid determining the desired pressure allowing
5 the tyre to be molded, also supplies heat necessary for vulcanisation.

It will be recognised that in the concerned method, during said expansion imposed to the tyre to complete
10 the molding and curing operations, the inner surface of same (preferably the liner and part of the beads) is in an elastic state, as already said, i.e. these tyre parts are partly cured for the above stated reasons.

15 In this case the inner tyre surface behaves like a vulcanisation bladder in a conventional vulcanisation method, wherein an inflatable bladder acts against the inner surface of a green tyre, manufactured without the aid of a toroidal support, for molding it against the
20 mold walls and distribute the elastomer material present in the different semifinished products in a substantially uniform manner.

Consequently, in the method of the invention, although
25 in the absence of an inflatable bladder, the inner tyre surface (preferably the liner) that already has good elasticity features, transmits the primary-working fluid pressure to the whole tyre in a substantially uniform manner and behaves like the inflatable bladder
30 of a traditional method. Therefore, thanks to a uniform molding, a vulcanised tyre substantially meeting the nominal design features is obtained.

Should said airtight device 200 be provided separated
35 from said mold 102, at the end of the step of

- 17 -

evacuating said secondary working fluid the tyre is extracted from said device in an automated or manual manner and is placed into a mold in which the molding and curing steps go on in a manner substantially
5 identical with the above described one.

It is to be noted that during the tyre-pressing step from the outside to the inside in order to press the inner tyre surface against the outer surface of the
10 toroidal support 10, heating of said inner tyre surface can be carried out by use of said primary working fluid under pressure conveyed through the toroidal support as previously illustrated, or by heating the toroidal support independently of use of said primary working
15 fluid, by means of electric resistors, for example. In the last-mentioned case pressure of the secondary working fluid can also be of few bars (even 2 or 3), provided the differential pressure keeps within the above stated range.

20

It will be finally recognised that in the method of the invention said step of pressing the inner surface of the green tyre 50 against said outer surface of the toroidal support 10 can take place indifferently
25 before, after or simultaneously with heating of said toroidal support.

C L A I M S

1. A method of molding and curing a tyre for vehicle wheels comprising the steps of: building a green tyre
5 (50) on a toroidal support (10) having an outer surface the shape of which substantially matches that of an inner surface of said green tyre (50); heating said toroidal support (10) to transmit heat to the inner surface of the tyre in contact with said toroidal
10 support (10); pressing said inner surface of said green tyre (50) against said outer surface of said toroidal support (10) through at least one secondary working fluid under pressure; pressing an outer surface of said green tyre (50) against the walls of a molding cavity
15 (104) defined in a vulcanisation mold (102), through a primary working fluid under pressure passing in at least one diffusion gap between said outer surface of said toroidal support (10) and said inner surface of said green tyre (50); said primary working fluid under
20 pressure being heated so as to supply heat to said green tyre (50) to cause vulcanisation of same.
2. A method as claimed in claim 1, wherein heating of said toroidal support (10) is carried out by means of
25 electric resistors.
3. A method as claimed in claim 1, wherein heating of said toroidal support (10) is carried out through said primary working fluid conveyed into said toroidal
30 support (10).
4. A method as claimed in claim 1, wherein during the step of pressing said inner surface of said green tyre (50) against said outer surface of said toroidal
35 support (10) by said secondary working fluid under

- 19 -

pressure, the pressure of said secondary working fluid is greater than the pressure of said primary working fluid.

5 5. A method as claimed in claim 4, wherein the pressure of said primary working fluid is less than 16 bars.

6. A method as claimed in claim 4 wherein the pressure of said secondary working fluid is included between 8
10 and 18 bars.

7. A method as claimed in claim 1, wherein during the step of pressing an outer surface of said green tyre (50) against the walls of said molding cavity (104) by
15 means of said primary working fluid, the pressure of said primary working fluid is included between 18 and 35 bars.

8. A method as claimed in claim 1, wherein the
20 temperature of said primary working fluid is included between 170°C and 210°C.

9. A method as claimed in claim 1, wherein said
25 primary working fluid comprises steam and nitrogen.

10. A method as claimed in claim 1, wherein said step of pressing said inner surface of said green tyre (50) against said outer surface of said toroidal support (10) comes before said step of heating said toroidal
30 support (10) in order to transmit heat to the inner surface of said tyre in contact with said toroidal support (10).

11. A method as claimed in claim 1, wherein said step
35 of pressing said inner surface of said green tyre (50)

against said outer surface of said toroidal support (10) comes after said step of heating said toroidal support (10) in order to transmit heat to the inner surface of said tyre in contact with said toroidal support (10).

12. A method as claimed in claim 1, wherein said step of pressing said inner surface of said green tyre (50) against said outer surface of said toroidal support (10) takes place substantially simultaneously with said step of heating said toroidal support (10) in order to transmit heat to the inner surface of said tyre in contact with said toroidal support (10).

13. An apparatus for molding and curing a tyre for vehicle wheels, said apparatus (101) comprising: an airtight vulcanisation mold (102) arranged to receive a toroidal support (10) adapted to support a green tyre (50) within a molding cavity (104); at least one passage device adapted to feed at least one primary working fluid under pressure, which is formed through said toroidal support (10) and opens onto the outer surface of same, so as to enable passage of said primary working fluid under pressure towards the inner surface of said green tyre (50); a feeding device to supply a secondary working fluid under pressure, which is operatively associated with said vulcanisation mold (102) to press said green tyre (50) from the outside to the inside onto said outer surface of said toroidal support (10); heating devices to heat said toroidal support (10); heating devices to heat said primary working fluid to transmit heat to said green tyre (50) and cause vulcanisation of same.

14. An apparatus as claimed in claim 13, wherein said

- 21 -

feeding device of a secondary working fluid under pressure comprises at least one delivery duct (108) and one discharge duct (109).

5 15. An apparatus as claimed in claim 13, wherein said primary working fluid is designed to heat said toroidal support (10).

10 16. An apparatus as claimed in claim 13, wherein said heating devices of said toroidal support (10) comprise electric resistors.

15 17. An apparatus as claimed in claim 13, wherein said airtight mold (102) comprises a lower half (102A) and an upper half (102B) in engagement with a base (103A) and a closing portion (103B) respectively, at least one circumferential seal (107) placed on the opposite surfaces of the two halves (102A, 102B) and a plurality of seals (106) placed close to vents intended for
20 release of said primary working fluid.

18. An apparatus for molding and curing a tyre for vehicle wheels, said apparatus (101) comprising: a vulcanisation mold arranged to receive a toroidal
25 support (10) adapted to support a green tyre (50) within a molding cavity; at least one passage device, adapted to feed at least one primary working fluid under pressure, which is formed through said toroidal support (10) and opens onto the outer surface of same,
30 so as to enable passage of said primary working fluid under pressure to the inner surface of said green tyre (50); heating devices to heat said primary working fluid to transmit heat to said green tyre (50) and cause vulcanisation of same; an airtight device (200)
35 arranged to receive said toroidal support (10); a

- 22 -

feeding device to supply a secondary working fluid under pressure which is operatively associated with said airtight device (200) for pressing said green tyre (50) from the outside to the inside onto said outer surface of said toroidal support (10); heating devices to heat said toroidal support (10).

19. An apparatus as claimed in claim 18, wherein said airtight device (200) comprises a lower half (202A) and an upper half (202B) in engagement with a base (203A) and a closing portion (203B) respectively, and at least one circumferential seal (207) placed on the opposite surfaces of the two halves (202A, 202B).

20. An apparatus as claimed in claim 18, wherein said feeding device of said secondary working fluid under pressure comprises at least one delivery duct (208) and one discharge duct (209) to respectively feed and evacuate said secondary working fluid within said device (200).

21. An apparatus as claimed in claim 18, wherein said airtight device (200) comprises at least one duct (210) for feeding said primary working fluid.

22. An apparatus as claimed in claim 18, wherein said heating devices of said toroidal support (10) comprise electric resistors.

1/4




FIG 1




FIG 2

3/4




FIG 3

4/4




FIG 4

INTERNATIONAL SEARCH REPORT

Inter application No
PC 1.1.10 2/04833

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B29D30/06 B29D30/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B29D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 976 533 A (PIRELLI) 2 February 2000 (2000-02-02) cited in the application paragraphs '0001!', '0002! paragraphs '0015!'-'0040! abstract; claims 1-23; figures 1-3	1-22
A	EP 0 928 680 A (PIRELLI) 14 July 1999 (1999-07-14) cited in the application abstract; figures 1-13	1-22
A	EP 1 038 657 A (PIRELLI PNEUMATICI) 27 September 2000 (2000-09-27) paragraphs '0001!', '0002! paragraphs '0017!'-'0049! abstract; claims 1-29; figures 1-5	1-22
	--- -/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

3 March 2003

Date of mailing of the international search report

19/03/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3018

Authorized officer

BRUNOLD, A

INTERNATIONAL SEARCH REPORT

Internu plication No
PCT, ID 02/04833

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 822 047 A (CONCEPTION ET DEVELOPPEMENT MICHELIN SA) 4 February 1998 (1998-02-04) column 7, line 55 -column 8, line 10 abstract; figures 2,5,6,9	1-22
A	DE 355 909 C (ERNEST HOPKINSON) 10 July 1922 (1922-07-10) the whole document	1-22
A	US 1 798 210 A (LAURSEN LAURITS A) 31 March 1931 (1931-03-31) page 1, line 9 -page 3, line 51 page 4, line 119 - line 129 claims 1-6; figures 1,3,4	1-22

INTERNATIONAL SEARCH REPORT

tion on patent family members

Intern: Application No
PCT/15 02/04833

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0976533	A	02-02-2000	EP 0976533 A2 AT 227209 T BR 9903255 A BR 9903300 A CN 1246404 A CN 1246405 A DE 69903772 D1 EP 0976534 A2 JP 2000052349 A JP 2000061945 A TR 9901821 A2 TR 9901822 A1 US 2002125615 A1 US 6409959 B1 US 6332999 B1	02-02-2000 15-11-2002 22-02-2000 21-03-2000 08-03-2000 08-03-2000 12-12-2002 02-02-2000 22-02-2000 29-02-2000 21-02-2000 21-02-2000 12-09-2002 25-06-2002 25-12-2001
EP 0928680	A	14-07-1999	EP 0928680 A1 BR 9805745 A CN 1225869 A JP 11314284 A TR 9802757 A1 TW 407107 B US 2002029841 A1	14-07-1999 08-03-2000 18-08-1999 16-11-1999 21-07-1999 01-10-2000 14-03-2002
EP 1038657	A	27-09-2000	EP 1038657 A1 AT 224296 T BR 0001423 A DE 60000463 D1 JP 2000296523 A US 6479008 B1	27-09-2000 15-10-2002 20-03-2001 24-10-2002 24-10-2000 12-11-2002
EP 0822047	A	04-02-1998	AU 720587 B2 AU 3240497 A BR 9704211 A CA 2211030 A1 CN 1174119 A DE 69716529 D1 EP 0822047 A1 JP 10076526 A US 6224808 B1	08-06-2000 05-02-1998 17-02-1999 01-02-1998 25-02-1998 28-11-2002 04-02-1998 24-03-1998 01-05-2001
DE 355909	C	10-07-1922	NONE	
US 1798210	A	31-03-1931	NONE	